

To Study the Properties of Concrete with Partial Replacement of Aggregates by Waste Plastic

Monu¹, Er Sumesh Jain²

¹M. Tech Scholar, ²Assistant Professor,

^{1,2}Department of Civil Engineering, OITM, Hisar, Haryana, India

ABSTRACT

Solid waste management is among the key environmental issues in India. The current research applies to the usage of or even recycled plastics as an alternative for rough aggregates in concrete. The primary goal of the analysis is to investigate the modification in the physical attributes of concrete by the inclusion of plastics to concrete. In addition to the physical qualities, winter qualities of the ensuing concrete may also be analyzed.

The utilization of plastic aggregates was discovered to lead to the development of sturdy concrete. Additionally, with the plastics, the tensile and compressive strength of the concrete reduces. The foremost change brought approximately by using plastics is the fact that concrete's thermal conductivity is decreased due to the utilization of plastics. It is able to thus be declared recycled plastics are usually utilized for thermal insulation of structures.

Series of experiments had been performed in this current study for a comparison of the usage of Used Plastic as a replacement of sand in various different proportions. The main conclusions drawn was that the compressive strength increases with the inclusion of Used Plastic upto a certain proportions and then reduces the strength.

How to cite this paper: Monu | Er Sumesh Jain "To Study the Properties of Concrete with Partial Replacement of Aggregates by Waste Plastic"

Published in International Journal of Trend in Scientific Research and Development (ijtsrd), ISSN: 2456-6470, Volume-4 | Issue-1, December 2019, pp.1162-1165, URL: www.ijtsrd.com/papers/ijtsrd29874.pdf



IJTSRD29874

Copyright © 2019 by author(s) and International Journal of Trend in Scientific Research and Development Journal. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (CC BY 4.0) (<http://creativecommons.org/licenses/by/4.0/>)



INTRODUCTION

A large focus has been centered on safeguarding and environmental natural resources as well as recycled wastes substances. In fact lots of industries are creating a number of products that include scrap (residues). Within from last twenty years, several types of research regarding the usage of numerous types of urban wastes materials in building components industrials process are published. Several researchers investigate that are already given to learn new sorts of waste materials to explore profoundly certain areas. Additionally, wastes aside from the environmental advantages definitely create consequences that are really good on the attributes of ultimate items.

Among the new waste supplies applied to the concrete industry that is reused clear plastic. For fixing disposal of a great amount of recycled plastic Substances, in concrete industry reuse of plastic material is viewed as probably the most achievable usage. Recycled plastic may be utilized as rough aggregate of concrete. Nevertheless, it's essential to underline that reusing of byproducts isn't however economically useful, on account of the top expenses of transportation and the effect on the overall expenses of output. Furthermore, it's essential never to overlook various other expenses, specifically referable towards byproducts type, in certain, to the demand of computing gas emission, throughout firing, and also the existence of deadly and contaminating components.

PLASTICS

The term "plastic" indicates material that has plasticity appropriately, something which is created in a gentle condition and utilized in a good state is referred to as a plastic material.

Thus, the foundation of plastic developing may be traced to the processing techniques of all-natural huge polymers for example tortoiseshell, tusks, horns, amber, shellac, lacquer, and inorganic materials like; metals, glass, and clay. Due to organic excessive polymer substances, they aren't even in quality as well as absence mass efficiency in instances that are a number of, coming from first times it's been required particularly in order to process them readily & into greater quality and also to substitute synthetic substances for all-natural huge polymers. Rayon, ebonite, synthetic rubber, and Celluloid are artificial substances. Now, it's identified the plastics are synthesized huge polymers that happen to have plasticity, as well as consequently materials made from these organic substances, are precluded. Plastics will be divided into 2 kinds. The first category is thermoplastic that could be melted for recycling in plastic industry. These are polyethyleneterephthalate, polytetrafluorethylene, polyoxymethylene, polyamide, polypropylene, and polyethylene.

LITERATURE REVIEW

Batayneh et al. (2017) discovered the impact of terrain plastic material on a concrete slump. Concrete mixes of approximately 20% plastic allergens are equal to changes in fine aggregates. The table shows the detailed results related to slump test as well as mixture proportions. It was noticed that slump is inversely proportional to the content of plastic particles. It also been noticed that slump has reduced to 25% when it is replaced by 20% of the initial slump having 0% plastic particle as revealed in Fig. 2.1. This reduction in value of slump is a result of plastic shape that means the plastic allergens have sharper edges as compared to fine aggregate. At 20% plastic particle content, the value of slump is calculated as 58mm. Therefore, this particular value may be acceptable as well as its mixture is also workable. Additionally, crushed concrete, glass, and plastics had also been utilized as replacing coarse aggregates which have been noticed that using crushed aggregates causes optimum slump minimization, whereas utilizing crushed glass has minimum impact on resulting slump concrete.

Zeng and Bayasi (2014) learned the consequences of polypropylene fibers on the slump as well as inverted slump cone period of concrete mixes. They found that with increase in plastic percentage, inverted slump cone period also increased. It was additionally found that 0.3% is the volume fractions of fibers, fiber impact on workability of fresh mix is irrelevant also quite inconsistent; as well as 0.5% for fiber amount, although, fibers came out to negatively impact new mix workability, much more apparent by the increased inverted slump cone period with nineteen mm fibers with a pronounced impact than 12.7 mm fibers.

Dalal, as well as Al-Manaseer (2012), identified concrete slump mixes produced with plastic aggregates. It was also found that there is increased in concrete slump if plastic-made aggregates have been incorporated. The concrete with 50% plastic material aggregates possessed a somewhat greater cone slump as compared to concrete with no clear plastic aggregates. In addition to the slump test, K slump test had also been performed. Consistency results of K-slump exhibited an equivalent design to which from the cone slump. They realized that the plastic aggregates neither assimilated neither absorbed water. As a result of this particular nonabsorptive attribute, concrete mixes that contain plastic aggregates are going to have much more complimentary water. So, the slump enhanced as revealed in Table 2.2.

Soroshian et al. (2013) claimed a decrease in slump with the usage of recycled plastic material in concrete. Fig.2.2 revealed results of Slump test. It's apparent the inclusion of any discrete reinforcement triggered slump damage. Whereas non slender plastic material particles, residue was shredded by automobile, and flakes have been worn for dosages which had been in order of magnitude of those of slender fibers, the results of theirs on new combination attributes have been similar. This might be due to the pronounced negative effects of slender fibers on new combination workability.

Hoi et al. (2015) investigated the effect of PET bottles WPLA lightweight aggregate on the concrete's workability. Combination ratios of concrete had been designed and so the water-cement proportions were 53%, 49%, and 45%, as well as the WPLA replacing ratio were 75%, 50%, 25%, and 0% by fine aggregate's volume. They found that slump importance of

misuse PET plastic bottles little aggregate concrete (WPLAC) enhanced with the increased replacing and water-cement ratio. The improvement workability ratios show 123%, 104%, and 52%, as compared to normal concrete at 53%, 49%, and 45% of water-cement ratios. This might be linked not only to the smooth and spherical condition but additionally to the absorption of WPLA.

Saradhi et al. (2014) proven fresh concrete with expanded plastics mixes proved much better flow values as compared to the regular concrete at comparable water-cement ratio, as well as absolutely no segregation, was found in virtually any incorporate despite the fact that the concretes were created without having the inclusion of binding ingredients. Besides, it was mentioned that the Expanded Plastics (EPS) aggregates are compressed throughout mixing process as well as the ensuing concrete's densities are usually above the created densities by approximately 50kg/m³ to 100kg/m³. This particular influence was mentioned much more in mixtures that contain the regular rough aggregate.

Elzafraney et al. (2015) realized that higher recycled information concrete made under area problems effectively for the performance needs of this project. Air content ASTM C-231 along with Slump ASTM C-143 mixtures had been assessed. For high-recycled-content along with normal concretes, the slump value was measured as 45mm and 60mm. For high-recycled-content along with normal concretes, air content value had been measured as 10.5% and 6% respectively.

Babu et al. (2014) learned that all of the expanded plastic mixes showed relaxed flow, as well as absolutely no segregation, was found in virtually any incorporate while in the concretes produced without having the inclusion of binding ingredients. Raghvan et al (1998) have claimed that mortars including rubberized shreds attained workability comparable to or even superior to a management mortar with no rubberized debris.

Bayomy and Khatib (2016) investigated the rubcrete's workability as well as stated that with a rise in percentage of rubber content, slump value decreases. The more observed that at 40% rubberized contents, slump was practically zero as well as concrete was not able to work. It had also been found that mixtures produced with fine crumb man-made materials had been much more practical compared to all those with rough tire potato chips or maybe a mix of tire fries as well as crumb man-made materials.

Hashmi, as well as ismail (2017), has discovered the slump is susceptible to reducing sharply with raising the waste plastic ratio as revealed in Fig.2.3. This particular reduction could be due to the point that several contaminants are angular and some have nonuniform styles leading to a lesser amount of fluidity. Despite the slump minimization, the misuse clear plastic concrete mixtures have simple workability and therefore are ideal to be used in huge websites and precast apps depending on the following consideration:

Naik and Siddique (2016) have claimed that mortars including rubberized shreds attained workability equivalent to or maybe superior to a management mortar with no rubberized debris It had also been found that mixtures

produced with fine crumb man-made materials had been much more workable compared to all those with rough tire potato chips or perhaps a mix of tire fries as well as crumb man-made materials.

Tests Done in Research

1. Test of concrete
 - A. Physical inspection of concrete
 - B. Workability
 - C. Compressive strength test
 - D. Split tensile strength test
 - E. Shear strength test
2. Test of aggregates
 - A. Abrasion resistance of aggregates
 - B. Impact resistance of aggregates
 - C. Crushing resistance of aggregates

Objectives

The effect of polyethylene as admixture on the strength of bituminous mix The present work is aimed at using two polymeric waste materials, such as polyethylene and tire fibers as reinforcement in concrete pavement. The basic objective of this work is to assess the advantages of using such waste materials such as increase in compressive, flexure and shear strength and reduce in deflection characteristics of the resultant concrete To study resistance to permanent deformation of mixes with and without polyethylene and also the determination of the deflection in the laboratory testing then its comparison to the theoretical deflection and check whether the errors are in the allowable limits of 20%.

Polyethylene and tire to achieve greater concrete strength properties in order to reuse them into something very useful and helping in reducing the environmental impact that the both of them have. The effect of polyethylene as admixture on the strength of bituminous mix with different filler and replacing some percentage of fine aggregate

Conclusion

The following would be the conclusions that may be created based on the experiments produced by several researchers:

1. Plastics could be utilized in a mixture of concrete to change several aggregates. This plays a significant role in decreasing concrete weight. As an application, it is useful for nonbearing lightweight concrete-like concrete sections employed in facades.
2. For a specified w/c, the usage of plastics in the mixture reduced the density, concrete's tensile strength as well as compressive strength.
3. In the plastic concrete case the impact of water-cement ratio is not noticeable. It's due to the reality that the clear plastic aggregates lessen the connect sturdiness of concrete. Thus, the disappointment of concrete happens because of disappointment of the bond between the cement paste and clear plastic aggregates.
4. In concrete, plastics introduction tends to create concrete ductile, thus raising the concrete's capability to considerably deform before breakdown. This particular distinctive can make the concrete helpful in situations in which it'll be put through strong temperatures like contraction and development, or maybe thaw and

freeze.

5. In concrete the addition of reused aggregates under study have been proven to be beneficial by an electricity purpose. The utilization of plastic aggregates useful to keep the inside cooler, if the exterior heat is elevated, as when compared with the control concrete.

REFERENCES

- [1] Al-Manaseer, A. A., T. R., Dalal., 1997. "Concrete containing plastic aggregates", Concrete International, 47- 52.
- [2] Ashraf, M., Ghaly, F., 2004. ASCE,1 and Michael S. Gill, A.M.ASCE2 "Journals of materials in civil engineering' © ASCE , 289-296.
- [3] Balaguru, P. N., Shah, S. P., 1992., "Fiber Reinforced Cement Composites". McGraw- Hill, Inc., 530 p.
- [4] Batayneh, M., Marie, I., Asi I., 2006. "Use of selected waste materials in concrete mixes". Waste Management (27) 1870-1876
- [5] Bayasi, Z., Zeng, J., 1993." Properties of polypropylene fiber reinforced concrete". ACI Materials Journal 90 (6), 605-610.
- [6] Benazzouk, A., Queneudec, M., 2002. "Durability of cement-rubber composites under freeze thaw cycles". Proceedings of the International Conference on Sustainable Concrete Construction, University of Dundee, Scotland, UK, pp. 356- 362
- [7] Boutemour, R., Taibi, M., Ouhib, N., Bali, A., 2004. "Investigation of the use of waste plastic as aggregate for concrete" In: International Conference, Sustainable Waste Management and Recycling: Challenges and Opportunities, 14-15. Thomas Telford Publishing, Thomas Telford Ltd., London, ISBN 0727732854.
- [8] Cheong, K. H. and Lee, S. C., 1993. "Strength of Retempered Concrete", ACI Materials J. **90** (3), 203-206
- [9] Choi, Y. W., Moon, D. J., Chung, J. S., Cho, S. K., 2005. "Effects of waste PET bottles aggregate on properties of concrete". Cement and Concrete Research 35, 776-781.
- [10] Eldin, N. N., 1993 Member, ASCE, and Ahmed B. Senouci, 2 Associate Member, ASCE., "Rubber-tire particles as concrete aggregates". Journal of Materials in Civil Engineering, Vol. 5, No. 4
- [11] Fattuhi, N. I., Clark, N. A., 1996. "Cement-based materials containing tire rubber". Journal of Construction and Building Materials 10 (4), 229-236.
- [12] Goulias, D. G., Ali, A. H., 1997. "Non-destructive evaluation of rubber modified concrete". In: Proceedings of a Special Conference, ASCE, New York, pp.111-120.
- [13] Hernandez-Olivares, F., Barluenga, G., Bollati, M., Witoszek, B., 2002. " Static and dynamic behavior of recycled tire rubber-filled concrete". Cement and Concrete Research 32 (10), 1587-1596.
- [14] Jain, R. K., Singh, Y., Rai, Mohan.,1977., "Recent Trends of Research in Plastic Building materials in India". Building and Environment, Vol. 12, pp. 277-280

- [15] Jo, B. W., Park, S. K., Park, J. C., 2007. "Mechanical properties of polymer concrete made with recycled PET and recycled concrete aggregates". Construction and Building Materials
- [16] Karim, S., Rebeiz, D., Fowler, W., Fellow, and Donald R. P., 1993. "Recycling plastics in polymer concrete for construction applications". Journal of Materials in Civil Engineering, Vol. 5, 237-248.
- [17] Khatib, Z. K., Bayomy, F. M., 1999. "Rubberized portland cement concrete" ASCE Journal of Materials in Civil Engineering 11 (3), 206-213.
- [18] Kline, C. (1989). "Plastics recycling take off in the USA." Chem. & Industry, 4(July), 440-442.
- [19] Mehta, P. K., Monteiro, P. M., 1993. Concrete: Structure, Properties, and Materials. Prentice Hall, 549
- [20] Naik, T. R., Singh, S. S., Brodersen, B. S., 1996. "Use of post-consumer waste plastics in cement-based composites". Cement and Concrete Research 26, 1489-1492.
- [21] Marzouk, O. Y., Dheilly R. M., Queneudec, M., 2007. "Valorization of post-consumer waste plastic in cementitious concrete composites". Waste Management (27) 310-318.
- [22] Marzouk, Y. O., 2005. "Valorisation of plastic bottle waste in cementitious concrete". Doctoral dissertation, University of Picardie Jules Verne, Laboratory of Innovative Technologies, EA 3899, Amiens, France.
- [23] Panyakapo. P., Panyakapo. M., 2007. "Reuse of thermosetting plastic waste for lightweight concrete." Waste Management.
- [24] Raghvan, D., Huynh, H., Ferraris, C.F., 1998. "Workability, mechanical properties and chemical stability of a recycled tire rubber-filled cementitious composite". Journal of Materials Science 33 (7), 1745-1752.
- [25] Saradhi Babua, D. T, Ganesh Babub, K. T.H. Wee., 2005. "Properties of lightweight expanded polystyrene aggregate concretes containing fly ash". Cement and Concrete Research (35) 1218- 1223.
- [26] Siddique, R., Naik, T. R., 2004. "Properties of concrete containing scrap-tire rubber – an overview". Waste Management (24) 563-569.
- [27] Soroushian, P., Mirza, F., Alhozaimy, A., 1995. "Permeability characteristics of polypropylene fiber reinforced concrete". ACI Materials Journal 92 (3), 291-295.
- [28] Tantala, M. W., Lepore, J. A., Zandi, I., 1996. "Quasi-elastic behavior of rubber included concrete". In: Ronald Mersky (Ed.), Proceedings of the 12th International Conference on Solid Waste Technology and Management, Philadelphia, PA.
- [29] Thayer, A. M., 1989. "Solid waste concerns spur plastic recycling efforts." Chem.& Energy. News, 67(5), 7-15.
- [30] Topcu, I. B., Avcular, N., 1997., " Analysis of rubberized concrete as a composite material". Cement and Concrete Research 27 (8), 1135- 1139.
- [31] Vaverka, J. V., 1991. "An analysis of reinforced concrete composite utilizing recycled polyethylene terephthalate thermoplastic". Doctoral dissertation, University of Northern Iowa, Cedar Falls, IA, University Microfilms International, LD2585.2.V39, 1991.
- [32] Zainab, Z. Ismail, E., Hashmi, A., 2007. "Use of waste plastic in concrete mixture as aggregate replacement" Waste Management
- [33] Zoorob, S. E., Suparma, L. B., 2000. "Laboratory design and investigation of the properties of continuously graded Asphaltic concrete containing recycled plastics aggregate replacement (Plastiphalt)". Cement & Concrete Composites (22) 233-242