Polymer Modified Steel Fiber Reinforced Concrete Bagasse

Varun¹, Dr. Sumesh Jain²

¹M.Tech Student, ²Professor,

^{1,2}Department of Civil Engineering, Om Institute of Technology & Management, Hisar, Haryana, India

ABSTRACT

This research describes the results of using modified concrete made from steel fibers in Styrene Butadiene Rubber (SBR). The study reported the different characteristics and compressive strength of latex reinforced steel fibre modified concrete. Latex modified concrete is known as portland cement and combined with polymers dispersed in water when mixed. This is considered a resin dispersion. Polymers such as natural rubber concrete latex increase resistance to carbonation and penetration of chloride. Polymer can boost properties such as higher strength and lower water permeability than standard concrete when used as an admixture. Because of a low strength level of concrete, steel fibers have been applied to concrete to enhance its stress characteristics. The concrete specimens of polymers were cast and tested to enhance certain mechanical and physical properties, such as friction, tensile strengths, bending strengths and operation efficiency. For our work, we used Styrene Butadiene rubber latex polymer and hooked end steel fibers. At an interval of 0,5%, the percentage of steel fibers used was 0 percent, 0,5%, 1 percent. In percentage 5 percent, 10 percent, 15 percent, was taken from the steel fiber produced best and latex produced maximum power. 24 beam (500 mm X 100 mm X 100 mm) is made of a total of 24 cubes, (150 mm x 150 mm X 150 mm). Checking of hardened concrete characteristics at 28th days. Few SFRC applications in the irrigation systems. Polymer-modified steel reinforced concrete is very resistant to weathering, so it is commonly used in pavement lying.

KEYWORDS: Betray, styrene butadiene rubber, steel fiber, bending power, friction, break tensile strength Development

INTRODUCTION

Concrete as a building material has great potential 45 is characterized as a composite material consisting of throughout the world, and only next to water consumption. Concrete is a composite material consisting of water, coarse granular material (fine and coarse aggregate or filler) embedded in a hard material matrix which fills the gap between the practical aggregate and collects it together. Concrete is commonly used in the manufacture of building buildings, frames, bricks, and walls. Concrete is used in large amounts almost everywhere that Mankind wants infrastructure. The worldwide use of concrete is twice that of steel, wood, plastic, and aluminum. Current world concrete consumption is estimated to be in the order of 14 billion tons per year. Large quantities of natural resources are required to meet this requirement, and day by day these natural resources are becoming depleted. Materials is the most commonly used type in construction materials with many attractive properties such as high compressive strength, rigidity, resilience under normal environmental conditions

The monomer is an organic molecular product that can chemically combine with molecules of the same or other product to form a high molecular weight substance known as polymer, which is known as polymerization as the mechanism by which they join. Adding latex to concrete increases the consistency of the material by which it manages crack ductility, resilience, impact and Fatigue, and resistance to carbonation. Reinforced concrete flooring is more effective than ordinary concrete cement flooring. "FRC How to cite this paper: Varun | Dr. Sumesh Jain "Polymer Modified Steel Fiber Reinforced Concrete Bagasse"

Published in International Journal of Trend in Scientific Research and Development (ijtsrd), ISSN: 2456-6470, Volume-4 | Issue-5, August 2020, pp.1724-1727,



URL:

www.ijtsrd.com/papers/ijtsrd33272.pdf

Copyright © 2020 by author(s) and International Journal of Trend in Scientific Research and Development Journal. This is an Open Access article distributed

under the terms of Creative the **Commons Attribution**



License (CC BY 4.0)(http://creativecommons.org/licenses/by /4.0)

concrete reinforced with discrete random but uniformly spaced short length fibers." The fibers may be of steel, polymer or natural materials. FRC is regarded as a material with improved properties and not as reinforced cement concrete, while reinforcement is provided to reinforce concrete locally in tension zone. In hardened concrete the primary function of steel fibers is to change the cracking process. By changing the process of cracking the macro cracking becomes a micro cracking. The cracks are smaller in width thereby decreasing the concrete's permeability and enhancing the concrete's overall cracking pressure. The fibers can bring a charge through the crack. In addition to minimizing permeability and increasing fatigue strength, a major benefit of using fiber reinforced concrete (FRC) is that fiber inclusion increases durability and load bearing capacity after the first crack in flexure behaviour. Developing countries are making every effort to achieve rapid development in the manufacturing and housing fields. Development requires comprehensive construction operations. Cement concrete; hitherto, given its many drawbacks, has been one of the essential building materials. For many superior properties over traditional cement concrete, the newly created "Polymer Concrete" is one of the most flexible building materials. In particular, polymer concrete is highly suitable for prefabricated building industry, irrigation systems, marine structures, nuclear power generation and desalination plants.

International Journal of Trend in Scientific Research and Development (IJTSRD) @ www.ijtsrd.com eISSN: 2456-6470

Historical development

The idea of polymer Cresson was already granted the first patent of the design in 1923. This patent applies to natural rubber latex paving materials, and cement has been used as a filler. In 1924 Lefebure issued the first patent with the present principle of polymer alteration. Since then, for 70 years or more, there has been significant research and development of polymer modification for cement, mortar, and concrete in different countries. As a result, several successful polymer modification systems have been developed for cement mortar and concrete, and are currently being used in various applications.

Polymer in concrete Some concrete polymers are;-Polymer concrete (PC) Polymer impregnated concrete (PIC) Polymer modified concrete or polymer

portland cement concrete (PMC or PPCC)

Because of its comparatively low cost and very comparable manufacturing techniques to traditional concrete, PMC is most commonly used of these three forms of polymeric material. The most widely used silicone resin is in PMC the first patent was used in paving materials in 1923 using natural rubber latexes. In the early 1930's, organic rubber was introduced for construction. But in the early 1960's, practical application of PMC only became popular.

Polymer Portland cement Concrete (PPCC)

ACI Concrete Practice Manual Section 5-1990[4] describes mixtures of Polymer Portland Cement Concrete (PPCC) as standard Portland Cement Concrete to which a water-soluble or emulsified polymer was applied during the mixing phase. The hardening of polymer often happens as the concrete recovers, creating a dense polymer layer in the concrete.

Principles of Polymer Modification

Whereas composites such as mortar and concrete cementations utilize admixtures dependent on polymers of either type, such as polymer latexes, water-soluble polymers, and liquid polymers. It is very necessary that both cement hydration and the formation of polymer films (polymer layer coalescence and resin polymerisation) proceed well to create a monolithic matrix method with network structure in which the hydrated cement cycle and the polymer phase interpenetrate, resulting in superior properties compared to conventional plastic cementations. Latex polymer modification in cement mortar and concrete is powered by both cement hydration and polymer film development.

LITERATURE REVIEW

Dr. D. L VenkateshBabu, To improve its tensioning properties, steel fibers were inserted into the concrete. The polymer concrete models were casted and tested with and without fibers to investigate the production of such mechanical and physical properties such as compressive forces, tensile strengths and workability. We used silicone Styrene Butadiene Rubber Latex and hooked end steel fibres in our work. They are latex 5 per cent SBR and steel fibers 0.5 per cent. The goods in reinforced concrete were tested in days 7 and 28. It was observed that the prescribed dose of fibers increased the early compressive strength of concrete but diminished the compressive force by 28 days. Steel fibers are used to increase the tensile strength of concrete Cement OPC Birla Super 53 style cement for our laboratory work.

Both cement assets as per code IS 12269: 1987 is tested for 53 grade ordinary Portland cement. Generic density of cement is 3.15. The first and final settling time for cement was determined to be 70 minutes, and 220 minutes respectively. The fineness and consistency of cement is known to be 1.5% to 30%.

Z. A. Siddhiqi et.al. The effects of His study notes the results of applying polymer SBR latex to concrete both in terms of compressive strength and water absorption. SBR latex is also found to improve the internal structure of modified latex concrete resulting in a significant 28-day reduction of the water absorption volume. A contrast has been found of modified concrete from SBR in controlled concrete. From the findings it is inferred that on 28 days an increase in compressive strength and decrease in water absorption was found, while on the 7th day the early compressive intensity had negative effects, and early water absorption was low. Specimens range from 5% to 10%, with polymer dosages up to 20%.

V. M. Sautaraja et al present a analysis to examine the properties of concrete which can be further improved by incorporating SBR polymer along with steel fiber. This paper notes that improvement in strength due to the combined application of steel fiber and polymer SBR latex in standard concrete results in improved strength, resilience, hardness, cracking tolerance and propagation of cracks. The effect of curing condition on th intensity obtaining composite properties has also been observed. The P / C ratio preserving steady steel fiber differed with 0.75 per cent rise and 1.5 per cent bet wt raise. In cement: a massive increase in compressive strength and ductility following splitting is introduced into concrete. Test effects were found with respect to flexure and compressive forces, the increase in flexural and compressive strength was more efficient in dry curing, while the strength decreased with wet curing. Therefore it is expected to be inferred that the power of concrete is harmful to wet curing. Decreased workability is balanced in polymeric materials under dry curing environment due to the introduction of steel fibres.

R. Radhakrishnan clarified the application of polymer to repair existing concrete structures to repair existing concrete structures. For restore systems for increase service life, the amount of available approaches and resources, but the degree of effectiveness of any concrete repair relies largely on the appropriate choice and method of repair material use. Repair techniques are largely based on water penetration resistance and structural tensile cracking. To research the impact of cementitious content on SBR latex. A blend ratio of mortar1:3 was rendered with additional SBR by weight of cement at 20 per cent. In terms of compressive strength and break tensile strength for patched cylinder a comparative analysis was performed between added SBR specimen and control specimen without SBR. Along with the effect of thermal cycling on patched concrete, sorptivity experiments were also taken. It is understood from the study result that SBR modified cement mortar has very high water penetration and that SBR as a bonding agent has strong tensile strength relative to cement slurry. A SBR as a additive and as a cement mortar bonding agent meets the criteria provided by the ASTM specification. Upon thermal cycling, SBR multiplier retains improved efficiency and thus proved to be a

Sivakumar. M. V. N notes that various polymers have a comparative impact on concrete structural properties. A mechanical and flexural properties of transformed concrete made from polymer were found in this research. Two separate forms of latex-styrene butadiene polymers and acrylic styrene were used with various dosages (0-20 percent) to independently alter concrete composites in each situation. A statistical analysis of the results for the 7th as well as the 28th day was performed. Wet curing method was carried out up to the test date for a validity of this experiment. It was also found that polymer dosages are suitable for 15 per cent polymer in both situations. Although supporting the efficacy of each polymer, it was understood that due to its small particle size and comparatively less viscosity, acrylic styrene was proved superior to latex polymer.

R. Wang The dose of polymer ranged from 0-25 percent. The effects of wet and dry cure were generally detected at different healing ages. Findings were compared with guided polymerless mortar. The substantial improvement in flexural, split tensile and compressive strength with the aircuring study was observed at a later age compared to watercuring specimens with. Top polymers price was 20 per cent. The greater early intensity and adhesion to old building materials allows rebuilding of the buildings simpler in the shortest practicable period. In concrete buildings the loose concrete is removed, and the resulting voids are filled with materials with strong early resistance. The polymer r modified mortar and concrete may be used for various methods of repair, rehabilitation and stabilization of concrete and masonry buildings depending on the shape and degree of harm caused by the earthquake. Using polymer in cement mortar renders the mortar workable, and improves arch and Sturdy's water cement ratio. At later ages, air cure is preferred to raise the severity of the higher dose.

Abdulkader Ismail A. AL. Hadithi et.al. In this study, the fiber percentage varies by weight of cement up to 1.5% as well as the acrylic polymer content varies as 3%, 7% and 10% by weight of cement. Significant curing of specimens borne by Folic process as minimum water sunk in curing. Test found showed an increase in all control structural properties with the inclusion of steel fibers. Although the introduction of acrylic polymers along with steel fiber has a greater effect than reinforced concrete constructed from steel fiber. There was an improvement in the compressive strength of reinforced concrete made from steel fiber (14.2 percent -29.2 percent), although an improvement in PMSFRC was observed (44.8- 86.64 percent). Splitting tensile strength was found to increase up to (50-91 percent) for concrete steel fibers, which in the case of PMSFRC tends to increase up to (102.4-124.7 percent). Related increments of flexural intensity were observed as (24.2-48.3 percent) for SFRC and (62-78 percent) for PMSFRC.7 percent of P / C with 1 percent difference of volume fraction was considered to be maximum.

Y. M. Ghugal. Established an experimental study of polymermodified cement mortars. The factors regarded were the healing age of the substance in polymer and the curing process. This researched the effect of polymer admixture on compressive, tensile breakage, flexural resistance and workability. The dose of polymer ranged from 0-25 percent. The effects of wet and dry cure were generally detected at

different healing ages. Findings were compared with guided polymerless mortar. The substantial improvement in flexural, split tensile and compressive strength with the aircuring study was observed at a later age compared to watercuring specimens with. Top polymers price was 20 per cent. The greater early intensity and adhesion to old building materials allows rebuilding of the buildings simpler in the shortest practicable period. In concrete buildings the loose concrete is removed, and the resulting voids are filled with materials with strong early resistance. The polymer r modified mortar and concrete may be used for various methods of repair, rehabilitation and stabilization of concrete and masonry buildings depending on the shape and degree of harm caused by the earthquake. Using polymer in cement mortar renders the mortar workable, and improves Sturdy's water cement ratio. At later ages, air cure is preferred to raise the severity of the higher dose. Thanks to significant changes in technical properties and durability, technologies have been effectively used to rehabilitate the damaged, demolished and subtracted concrete and masonry buildings to be restored and rebuilt in the shortest possible time.

Materials and Methodology

The materials used for the preparation of concrete

- Cement
- Fine aggregate
- Coarse aggregate
- Steel fiber
 Styrene-but
 - Styrene-butadiene rubber (SBR)
- Superplasticizer
- silica fumeWater

To investigate the properties and suitability Of the fine aggregate for the intended application, the following tests were carried out.

- Workability
- Slump Test
- VeBe Test
- Compressive strength.
- Density of concrete.
- Flexural Strength

REFERENCES

- G. D. Awchat, N. M. Kanhe, Experimental Studies Modified Steel Fiber Reinforced Recycled Aggregate Concrete, International Journal Application or Innovation in Engineering & Management (IJAIEM). (2015)
- [2] Prof. Dr. Bayan S. Al-Nu'man and Dr. Abdulkader Ismail Al-Hadithi, Flexural Behaviour of Polymer Modified Beams, Journal of Engineering and Development, Vol. 13, No. 1, March (2009) ISSN 1813-7822.
- [3] Dr. K. M Soni, "Fiber Reinforced Concrete in Pavements", NBM&CW vol 12, pp 178- 181, May 2007.
- [4] Dr. S. S. Seehra, An Innovative concrete technological development of fully mechanized construction of cement concrete pavement", NBM&BW vol 12 pp76-93, March 2007.
- [5] Gopal Krishna, Key role of chemical admixtures for pavement quality concrete", NBM&BW vol 13, pp166-169, July 2007

International Journal of Trend in Scientific Research and Development (IJTSRD) @ www.ijtsrd.com eISSN: 2456-6470

- [6] J. M. L. Reis" Fracture and flexure characterization of natural fibers-reinforced polymer concrete" Construction and Building Materials vol 20 pp 673-678, Nov 2006
- [7] Amnon Katz, "Environmental impact of steel and FRP reinforced polymer", Journal for composite for construction vol 8 no.6 pp 48-488., Nov/Dec 2004.
- [8] M S Shetty "concrete Technology" S Chand Publication 1982 12th Editio, 2007.
- [9] en.wikipedia.orhttp://cedb.asce.org/cgi/wwwdisplay.c g(12sep2007).
- [10] The code IRC: 44-2008 "for cement concrete mix designs for pavements with fibers"
- [11] IS 10262: 2009 Indian Standard Guidelines for Concrete mix design.
- [12] IS 383: 1970 Indian Standard specifications for coarse and fine aggregate from natural sources for concrete.

- [13] CSIR-Central building research institute Roorkee
- [14] Textbook on Concrete Technology by ML Gambhir.
- [15] Nguyen Van, steel fibre reinforced concrete.
- [16] www.nbmcw.com/articles/concrete/26929
- [17] courses.washington.edu/cm425/frc.pdf
- [18] http://theconstructor.org/concrete/fibre avements/4781/
- [19] KENNETH G. BUDHINSKI, MICHEL K. BUDHINSKI," Engineering materials- Properties & selection", 8th edition, Prentice Hall India, pp 194-195
- [20] B. K. AGRAWAL, Introduction to Engineering Materials", 4th edition, Tata Mc Grawhill Publishing company ltd, pp194-195

