

# Utilization of Banana Peel Powder in Concrete

Rahul Mohabe<sup>1</sup>, G. D. Dhawade<sup>2</sup>, R. K. Kakkure<sup>3</sup>

<sup>1</sup>Student, <sup>2</sup>Professor, <sup>3</sup>Teacher,

<sup>1, 2, 3</sup>Bapurao Deshmuk College of Engineering, Sevagram, Wardha, Maharashtra, India

## ABSTRACT

Analysis of properties of concrete using banana peel as admixture is studied and verified the strength of concrete and temperature emitted due to chemical reaction to the normal Portland cement. The percentage of transmission temperature and reduction time of temperature has decreased; hence it is clear that the exothermal reaction in concrete has been reduced by using dried banana peel powder as admixture. The percentage of transmission temperature and reduction time of temperature has decreased; hence it is clear that the exothermal reaction in concrete has been reduced by using dried banana peel powder as admixture. Ingredients other than cement, water & aggregates that impart a specific quality to either plastic (fresh) mix or the hardened concrete (ASTMC 496) is called concrete admixture. The flexural strength of concrete by using banana peel powder as admixture has increased, but considerable lesser compressive strength has increased.

**KEYWORDS:** Green; compressed Earthen Block (CED); Green- Compressed... Portland cement (OPC), and banana fibers

**How to cite this paper:** Rahul Mohabe | G. D. Dhawade | R. K. Kakkure "Utilization of Banana Peel Powder in Concrete" Published in International Journal of Trend in Scientific Research and Development (ijtsrd), ISSN: 2456-6470, Volume-5 | Issue-4, June 2021, pp.150-151, URL: www.ijtsrd.com/papers/ijtsrd41186.pdf



IJTSRD41186

URL:

Copyright © 2021 by author(s) and International Journal of Trend in Scientific Research and Development Journal. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (CC BY 4.0) (<http://creativecommons.org/licenses/by/4.0>)



## INTRODUCTION

Banana is a type of fruit from herbaceous plants of the genus *Musa*. *Musa* species grow in a wide range of environments and have varied human uses, ranging from the edible bananas and plantains of the tropics to cold-hardy fiber and ornamental plants. Which is very rich in fiber content, About 30-35% of total mass of fibers and carbohydrates. Mineral content in a banana peel is primarily consistent of potassium (78.10mg/g) and manganese (76.20mg/g). Other minerals present are sodium, calcium and iron at 24.30, 19.20 & 0.61mg/g respectively. Bananas peels has numerous applications, for water purification. Bananas are grown in at least 107 countries. Although the wild species have fruits with numerous large, hard seeds, virtually all culinary bananas have seedless fruits. Bananas are classified either as dessert bananas (meaning they are yellow and fully ripe when eaten) or as green cooking bananas.

## AIM & OBJECTIVE

The general objective of this study is to investigate the compressive strength of concrete banana fiber as cementitious to produce high strength concrete with different temperature. The specific objectives of this study were: To determine the compressive strength of concrete using banana fiber ash as waste agriculture with various temperature. To determine the chemical properties of banana fiber ash burning with different temperatures as cement replacement. The purpose of this chapter is to study and analyze the previous study that has been done earlier through journals, (International Research Journal of Engineering and Technology (IRJET)) articles, p-ISSN: 2395-0056, p-ISSN: 2395-0072 research papers and also thesis.

This chapter will review more detail regarding banana fiber ash, its advantages and analyze more valuable information. Concrete is widely used in construction industry such as high rise building, bridge, houses, and others due to its durability.

## CONCLUSION ON LITERATURE SURVEY

1. In this project 2.5 % and 3.5% faster than as compare to normal concrete.
2. All grades of concrete. hence banana peel can be used as admixture where temperature due to exothermal reaction place an important role to exothermal reaction place an important role and to be reduced un construction.
3. Temperature transmittance capacity found more or less same for all grades.

## RESEARCH METHODOLOGY

- The banana peel is collected from different sources. As banana undergoes bio-degradation to avoid it peels are dried under sunlight for 2days.
- After complete drying the peels are powdered carefully. Obtained powder is packed in aluminum sheets or polythene cover helps in protecting powder from atmospheric moisture. While mixing the powder must be free from lumps. An empty spaced cube with bottom, size of 10\*10\*10cm casted using concrete with peel powder concrete and walls of thickness 1cm.
- Water of 1000 c was filled in empty cube and the time consumed for reduction of temperature of water to 400c

were noted down. This gives the time consumed by cube to reduce inner temperature of 1000 c of water to 400 c.

- An empty cube casted by using peel powder concrete size 10\*10\*10 was inserted into another larger empty cube casted using plane cement concrete size of 15\*15\*10cm.
- 3cm sufficient space was left between two cubes was filled with Water of 100c and top side of cube was closed by lid. Water temperature was noted down after 8mins for 1,3,7,21,23 and 28 days of similar casted samples.
- The difference between the water temperature noted after 8min and the temperature at room temperature gives the amount of heat transmitted through the walls of inner cube.

## REFERENCES

- [1] Derived from: "FAOSTAT". Food and agriculture organization of United Nations. The data for were combined as the two are distinguishing by some countries but combined under "bananas" by others.
- [2] G. M. Babatunde; "Availability of banana and plantain products for animal feeding". In: D. Machin, S. Nyvoid: Roots, tubers, plantains and bananas in animal feeding. Proceedings of the FAO Expert Consultation held in CIAT, Cali, Colombia FAO ANIMAL PRODUCTION AND HEALTH PAPER 95, FAO, Rome,1992.
- [3] A. Chaparadza, JM Hossenloppl; adsorption Kinetics, isotherms and thermodynamics of atrazine removal using a banana peel based sorbent. *Water-Science technology*, 65(5), 2012, PP. 940-947.
- [4] HS Oberoi, PV Vadlani, L. Saida, S. Bansal; ethanol production from banana peel using statistically optimized simultaneous scarification and fermentation process. *Waste management* 31(7), 2011, pp1576-1584.
- [5] Hai-Yan Sun, Li Juanhua, Pingjuan Zhao Ming Peng; Banana peel. Novel substrates for cellulose production under solid state fermentation *African Journal of Biotechnology* 10(77), 2011, pp. 1788.
- [6] V. Vivekanand, P. Dwivedi, N. Pareek, RP Singh; Banana Peel: potential substrates for laccase production by *Aspergillus Fumigatus* VKJ2. 4. 5 in solid-state Fermentation. *Applied BioChemistry and Bio-Technology* 165(1), 2011, pp. 204-220.
- [7] "How to use banana peels in your gardens". *Frugal Chicken* 2015-07-05. Retrieved 2015-07-06.
- [8] British Cement Association. (1994). Foamed Concrete Composition and Properties. 165-168. British Cement Association.
- [9] Fathilah, N. N. F. M. & Tan, C. S. Flexural Strength of Lightweight Foamed Concrete using cement to sand ratio 3 :1 with Inclusion of Polypropylene Fibre, 270-279.
- [10] Jitchaiyaphum, K., Sinsiri, T., & Chindaprasirt, P. (2011). Cellular lightweight concrete containing pozzolan materials. *Procedia Engineering*, 14, 1157-1164.
- [11] M. A. Othuman Mydin, N. Mohamad, A. A. Abdul Samad, I. Johari, and M. A. Che Munaaim. Durability performance of foamed concrete strengthened with chemical treated (NaOH) coconut fiber. *Proceeding of the 3rd International Conference on Applied Science and technology (ICAST 18)*. AIP Publishing. 20
- [12] Noridah Mohamad, Muhamad Afif Iman, MA Othuman Mydin, A A A Samad, JA Rosli1 and A. Noorwirdawati. Mechanical properties and flexure behaviour of lightweight foamed concrete incorporating coir fibre. *IOP Conf. Series: Earth and Environmental Science, IconCees 2017*. IOP Publishing.
- [13] Solomon Ikechukwu Anowai1 and Olorunmeye Fredrick Job. Durability properties of banana fibre reinforced ash concrete. *International Research Journal of Engineering and Technology (IRJET)*. Vol 4 (11), Pp 1169- 1174
- [14] Vishal Gadgihalli, Meena Y. R, Sindhu Shankar, Raghavendra Prasad Havanje Dinakar, S. C. Sharma. Analysis of properties of concrete using dried banana peel powder as admixture. *International Journal of Research - Granthaalayah*, 5(11), 351-354. 2017.
- [15] Daud, Z., Abubakar, M. H., Abdul Latiff, A. A., Awang, H., Ahmad, Z., Ridzuan, M. B., Cod and ammonia removal from landfill leachate using mixed granular adsorbent media. *Jurnal Teknologi*, 80 (4), (2018), pp. 81-86.
- [16] Daud, Z., Hatta, M. Z. M., Kassim, A. S. M., Aripin, A. M., Awang, H., Analysis of Napier grass (*Pennisetum purpureum*) as a potential alternative fibre in paper industry. *Materials Research Innovations*, 18, (2014), pp. S6-18-S6-20.
- [17] Daud, Z., Awang, H., Mohd Kassim, A. S., Mohd Hatta, M. Z., Mohd Aripin, A., Cocoa Pod Husk and Corn Stalk: Alternative Paper Fibres Study on Chemical Characterization and Morphological Structures. *Advanced Materials Research, Volume 911*, (2014), pp. 331-335.
- [18] Daud, Z., Awang, H., Kassim, A. S. M., Hatta, M. Z. M. & Aripin, A. M., Comparison of pineapple leaf and cassava peel by chemical properties and morphology characterization. *Advanced Materials Research. Volume 974*, (2014), pp. 384-388.
- [19] Habeeb, S. A., Latiff, A. A. A., Daud, Z., Ahmad, Z. The start-up of hybrid, anaerobic up-flow sludge blanket (HUASB) under a range of mesophilic and thermophilic temperatures. *EnvironmentAsia, Volume 4 (2)*, (2011), pp. 63-68.
- [20] Daud, Z., Aziz, H. A., Adlan, M. N., Hung, Y. -T., Application of combined filtration and coagulation for semi-aerobic leachate treatment. *International Journal of Environment and Waste Management, Volume 4 (3-4)*, (2009), pp. 457-469.