

## Review of Design and Analysis of Piston

Manu Singhasth<sup>1</sup>, Mrs. Poonam Diwan<sup>2</sup>

<sup>1</sup>M Tech (Machine Design) Student, Department of Mechanical Engineering, Vishwavidyalaya Engineering College Ambikapur, Chhattisgarh Vivekanand Technical University, Bhilai, Chhattisgarh, India

<sup>2</sup>Assistant Professor, Department of Mechanical Engineering, Vishwavidyalaya Engineering College Ambikapur Chhattisgarh Vivekanand Technical University, Bhilai, Chhattisgarh, India

### ABSTRACT

The piston is one of the vital components of IC engine which is subjected to pressure exerted by fuel combustion. Continuous subjection to thermal and structural loads causes failures in piston. The current research reviews various researches conducted to investigate the type and causes of damages developed in piston. The study on effect of piston material, coating material and tribological behavior on piston structural characteristics are presented by various scholars. The researchers have used both experimental and numerical techniques in investigation of piston failures.

**Keywords:** Piston failure, structural, thermal

**How to cite this paper:** Manu Singhasth | Mrs. Poonam Diwan "Review of Design and Analysis of Piston" Published in International Journal of Trend in Scientific Research and Development (ijtsrd), ISSN: 2456-6470, Volume-5 | Issue-6, October 2021, pp.1283-1286, URL: www.ijtsrd.com/papers/ijtsrd47572.pdf



Copyright © 2021 by author (s) and International Journal of Trend in Scientific Research and Development Journal. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (CC BY 4.0) (<http://creativecommons.org/licenses/by/4.0>)



### 1. INTRODUCTION

The current automotive industry demands for light weight engines which could enhance fuel efficiency and generate higher power. The weight reduction of engine is possible by using lightweight materials having high strength and thermal resistance. The materials include increased use of "lightweight materials, such as advanced ultra-high tensile strength steels, aluminum and magnesium alloys, polymers, and carbon-fiber reinforced composite materials" [1].



Figure 1: Piston design [1]

The piston is one of the critical components of engine which is subjected to high pressure from exhaust gases generated from fuel combustion. The major cause of piston failure is due to mechanical stresses or thermal stresses. The piston bears maximum pressure as compared to other parts of engine [1]. The use of lightweight materials can be used to achieve 20% to 40% weight without much compromise in strength of piston

### 2. LITERATURE REVIEW

U. I. Sjodin, U.L. O. Olofsson [1] has investigated initial sliding wear on a piston ring in a radial piston hydraulic motor. The initial sliding wear during running in of a piston ring used in the form of change of mass and surface roughness investigated. The down motion test rig was developed. Mild wear and sever wear are two types of wear in which mild wear has soft surface that is smoother than the original surface and sever wear forceful surface than original surface. The wear on the piston ring is on the top of the asymmetric topmost at the outer surface contacting the cylinder bore. The result is initially

roughness amplitude decreases rapidly, and has decreased by one-third after a sliding distance of 10m. There can be seen that from the fig that mass loss as sliding distance increased.

Simon C. Tung and Young Huang [2] have studied the modeling of wear progression of the piston ring cylinder bore system. The aim of this research is to develop an abrasive wear model for the piston ring cylinder bore system during study state operation. There was temperature, load, oil degradation, surface roughness and material properties considered as parameters.

John J. Truhan, Jun Qub, Peter J. Blau b [3] have studied on the effect of oil condition and its effect on the friction and wear of piston ring and cylinder liner materials in a reciprocating bench test. The investigation on an improved laboratory test to evaluate the friction and wear behavior of ring and liner material by using realistic (engine conditioned) lubricants. Wear can be expressed as mass loss, volume loss, or depth of wear. Wear depth is good for wear measurement with compare to other method. As the piston is lowered, the load decreases and wear is reduced. There is only small element of piston ring on top position which experiences wear. The viscosity has a minor effect on ring and flat (liner) friction in the boundary lubricated regime. Viscosity is affected by the soot content and level of oxidation, which could have implications for oil film thickness and pumping losses. The soot and particulate content have a major effect on wear of the cast iron flat and less of an effect on the ring for the materials studied here.

Zheng Ma et al [4] have studied on the model for wear and friction in cylinder liners and piston rings. The model can predict the effects of surface roughness, asperity contact, and temperature-pressure-viscosity on wear, lubrication and friction of the piston rings and cylinder liner. Wear is predicted based on the surface asperity contact pressure. The major wear mechanism of the cylinder liner wear is abrasion, in top portion during the break-in period. So the Archard wear model is selected for the wear calculation. Oil viscosity decreases at higher temperature. There was the engine speed and load increased step by step from a low level to the full load, full speed condition in 14 break-in-steps. There is observed that there is good agreement between the predicted cylinder bore wear and measurement bore wear. It is also observed that the minimum oil film thickness decreases during the engine break-in-period.

Edward H. Smith [5] has optimizing the design of a piston ring pack using DOE methods. Here ten factors are varied-six describing the ring profile, three ring

tensions, & the lubricant viscosity. The work describe in the paper is divided into three part. Design 1: Factors 1-4 were varied, with factors 5-10 fixed at their values in the real engine. Engine speed was 2500rpm Design 2: with engine speed of 3500rpm. Design 3: Factor 1-10 was varied. Engine speed was 2500rpm.

Murat Kapsiz, Mesut Durat, Ferit Ficici [6] the author had studied friction and wear between cylinder liner and piston ring pair using Taguchi design method. Here parameters are optimized for minimum weight-loss sliding velocity applied load and oil type. The Taguchi design method for two factors at two levels and one factor at four levels was used for the consideration of the plan of experiments.

P. C. Nautiyal et al [7] the author have developed an analytical model has been proposed to predict quantitatively the ring wear based on boundary lubrication principles. A quantitative assessment of the friction behavior using actual piston ring and liner combinations under conditions close to tdc of the engine was made so as to the mechanism of wear in a running engine. It has been recognized the maximum wear severity occurs at tdc when the system is working under boundary lubrication.

M. Priest et al [8] here a numerical model has been developed that predicts the dynamics, lubrication and wear of piston ring interactively for first time. The analysis is divided into two parts. First the model is used to predict the lubrication performance of measured ring packs before & after period of running at constant speed and load: the objective being to establish to change in tribological behavior with observed wear in engine. Secondly, the model is used to predict the lubrication and wear of the top compression ring from the same engine, with the objective of evaluating the correlation between the new model & experiments. The surface roughness of the piston rings & cylinder wall reduced dramatically over starting period. Wear of the new top compression ring was predicted to occur for much of the engine cycle with largest wear rates around top dead centre firing, where the applied loads are high and film thickness low. The understanding of piston ring profile evolution with time and its dependence on complex interactions between lubrication and wear. The lubrication prediction for measured ring profile have highlighted the sensitivity of lubricant film thickness and friction between the piston ring and cylinder wall, to wear of the ring profiles.

U.I. Sjodin, U.L.-O. Olofsson [9] have investigated on the wear interaction between piston ring & piston groove in a radial piston hydraulic motor was studied in regard to mass loss and changes in form and

surface roughness. There was a test rig developed which simulates the tilting movements of pistons at the end of strokes. There were a full factorial with center points design method is used. The wear mechanism is mild wear and piston groove showed a more wear than the piston ring.

L.M. Yang et al [10] has study of a wear model for assessing the reliability of wave energy convertor. For the study point absorber has been chosen. The convertor has been modeled by using bond graphs a systematic and useful method for systems spanning several energy domains. Here, an abrasive wear model for the piston ring and cylinder is developed during steady state operation.

Andrzej Adamkiewicz and Jan Drzewieniecki [11] have study on operational evaluation of piston ring wear in large marine diesel engine based on inspection through cylinder liner scavenge ports. There were two verification method of piston ring wear in which, first visual evaluation of piston ring wear & condition through scavenge port. Second estimation of piston ring wear amount by piston ring gap measurement. Third alternative methods for a wear of piston rings rely on measurement of run-in coating on their surfaces.

S.G. Fritz and G.R. Cataldi [12] have determined in situation piston ring wear in a single cylinder Medium Speed diesel engine using thin film surface layer activation (SLA). The top compression ring wear was quantified over a 500-hour test period for three different types of cylinder liner surface finishing technique. There are lubricating oil consumption rates and motoring friction horsepower requirements were determined.

M. Afzaal, Malik et al [13] have study on to develop hydrodynamic piston top ring lubrication model in initial engine start up by incorporating an elliptical cylinder wear manufacturing error and cylinder head clamping force. The numerical analysis is done based on two dimensional Reynolds equations. There is hydrodynamic pressure field generation & time based lubricating film thickness profile as function of crank rotation are examined and influence of bore out of roundness effect at time of engine startup are investigated. The hydrodynamic film and pressure profile is getting affected due to non-circular bore. From the numerical simulation, the minimum film thickness increases with non-circular bore.

Pavel Novotny [14] has demonstrated the principles of the numerical solution of piston ring dynamics. It considers in mixed lubrication conditions incorporating in a virtual engine & experimental inputs. The computational solution of piston ring

dynamics is a very complex problem. It requires multiple numerical approaches supplemented by suitable inputs. For the solution diesel turbocharged engine with three piston ring configuration used. The new simulation algorithm of piston ring dynamics has been developed and incorporated into Ring Dyn user guided interface. The algorithm is very fast it enables to calculate results during few seconds.

Claudia Lenauer, Christian Tomastik et al [15] have investigation on the effect of bioethanol on the piston ring – cylinder liner system; the tribological tests were carried out on a model tribometer set up, and measuring friction and piston ring wear. Here two types of lubricants fresh and altered were used. The fresh lubricants lead to a lower amount of running in wear and a higher steady-state wear rate. All altered oils lead to a higher amount of running in wear and a lower steady state wear rates than for the fresh oils. A comparison between the result of the tribometer wear measurements and the wear in the real combustion engine environment shows that the trend observed in the engine was replicated in the tribometer. The tribofilm thickness and the wear behavior correlate. The lower steady-state wear rates for the piston rings have a thinner tribofilm on the cylinder liners.

J. Michalski, P. Wos [16] have reports on the effect of cylinder liner surface topography on abrasive wear of piston cylinder assembly in combustion engine. Here engine tests were done on a dynamometer stand and they included 10h of fired running in period and 21h operation of intensified abrasive wear in piston cylinder assembly. Here the distinctions between piston–cylinder assemblies wear of the engines varied by cylinder liner roughness parameters due to different honing settings made. It was noticed that after 10 h of running-in operation the high correlation of the maximum valley depth of the profile with the piston–cylinder assembly wear.

Ferit Fıçıcı, Sezer Kurgun [17] has study on the experimental optimization of wear parameters of piston ring coated with molybdenum. Parameters optimize for minimum weight loss based on L27 Taguchi design with three parameters load, temperature and revolution with three levels.

John J. Truhan, Jun Qu et al [18] have studied on the laboratory test to evaluate piston ring and cylinder liner materials for their friction and wear behavior in realistic engine oils. Here wear test were carried out at 240N for 6h at 1000<sup>0</sup> C with new ring segments. A ring segment was tested against a flat specimen of gray cast iron typical of cylinder liner. Different lubricants like Jet A aviation fuel, mineral oil and a new and engine-aged, fully formulated 15W40 heavy duty oil were used to evaluate the sensitivity of



lubricant condition. Wear was measured by weight loss wear volume and wear depth using a geometric model. The result shows that Jet A has higher wear & used 15W40 oil showed least wear.

### 3. CONCLUSION

The existing researches conducted on piston have shown that oil condition, coating material, cylinder liner material on piston wear. The tribological studies were conducted and it was found that only small element of piston ring on top position which experiences wear. The effect of viscosity was also investigated and it was observed that oil film thickness has significant effect on the wear behavior of piston crown region and piston skirt region. The soot and particulate content have a major effect on wear of the cast iron piston ring.

### REFERENCES

- [1] U. I. Sjodin, U. I. O. Olofsson, "Initial sliding wear on piston rings in a radial piston hydraulic motor," Royal Institute of Technology, Sweden, *Wear* 254, pp. 1208-1251, 2003.
- [2] Simon C. Tung, Yong Huang, "Modeling of Abrasive Wear in a Piston Ring and Engine Cylinder Bore System," *Tribology Transactions* 47, pp. 17-22, 2004.
- [3] John J. Truhan, Jun Qu, Peter J. Blau, "The effect of lubricating oil condition on the friction and wear of piston ring and cylinder liner materials in a reciprocating bench test," *Wear* 259, pp. 1048-1055, 2005.
- [4] Zheng Ma, Naeim A. Henein, Walter Beyzik, "A model for wear and friction in cylinder liners and piston rings," *Tribology Transaction* 49, volume 3, pp. 315-327, 2006.
- [5] Edward H. Smith, "Optimizing the design of a piston-ring pack using DoE methods," *Tribology international* 44, pp. 29-44, 2011.
- [6] Murat Kapsiz, Mesut Durat, Ferit Fici, "Friction and wear studies between cylinder liner and piston ring pair using Taguchi design method," *Advances in Engineering Software* 42, pp. 595-603, 2011.
- [7] P. C. Nautiyal, S. Singhal and J. P. Sharmat, "Friction and wear processes in piston," pp. 43-49.
- [8] M. Priest, D. Dowson, C. M. Taylor, "Predictive wear modeling of lubricated piston rings in a diesel engine," UK, *Wear* 231, pp. 89-101, March 1999.
- [9] U. I. Sjodin, U. I. Olofsson, "Experimental study of wear interaction between piston ring and piston groove in a radial piston hydraulic motor," *Wear* 257, pp. 1281-1287, 2004.
- [10] L. M. Yang, J. Hals and T. Moan, "A wear model for assessing the reliability of wave energy converter in heave with hydraulic power takeoff," *Proceedings of the 8th European Wave and Tidal Energy Conference*, Uppsala, Sweden, pp. 874-881, 2009.
- [11] Andrzej Adamkiewicz, Jan Drzwieniecki, "Operational evaluation of piston ring wear in large marine diesel engine," *Journal of Polish CIMAC*.
- [12] S. G. Fritz, G. R. Cataldi, "In situ piston ring wear measurements in a medium speed diesel engine," *Journal of the society of tribologists and lubrication engineers* Volume 46, PP. 365-370, 1989.
- [13] M. Afzaal Malik, Ali Usman, S. A. Qasim, Riaz Mufti, "Modeling of piston top ring lubrication by considering cylinder out-of-roundness in initial Engine start-up," *Proceeding of the world congress on engineering* volume 2, London U. K. , 2010.
- [14] Pavel Novotny, Vaclav Pistex, Lubomir Drapal, "Modeling of piston ring pack dynamics," pp. 8-12, 2011.
- [15] Claudia Lenauer, Christian Tomastik, Thomas Wopelka, Martin Jech, "Piston ring wear and cylinder liner tribofilm in tribotest with lubricant artificially altered with ethanol combustion products," *Austrian Center of Competence for Tribology*, Austria, pp. 1-8, 2014.
- [16] J. Michalski, P. Wos, "The effect of cylinder liner surface topography on abrasive wear of piston – cylinder assembly in combustion engine," *Wear* 271, pp. 582-589, 2011.
- [17] John J. Truhan, Jun Qu, Peter J. Blau, "A rig test to measure friction and wear of heavy duty diesel engine piston rings and cylinder liners using realistic lubricants," *Tribology International* 38, pp. 211-218, 2005.
- [18] Ferit Fici, Sezer Kurgun, "Experimental optimization of wear parameters of piston ring coated with molybdenum," *Turkish Journal of Engineering, Science and Technology* 03, pp. 116-122, 2014.